

06-22-00 526 Rec'd PCT/PTO 21 JUN 2008 CT \$

FORM PTO-1367 (Modified) (REV 10-95)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE		ATTORNEY'S DOCKET NUMBER <b>AD-6547-A</b>	
<b>TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371</b>				U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR) <b>09/582483</b>	
INTERNATIONAL APPLICATION NO. <b>PCT/US98/27428</b>		INTERNATIONAL FILING DATE <b>23 DECEMBER 1998 (23.12.98)</b>		PRIORITY DATE CLAIMED <b>24 DECEMBER 1997 (24.12.97)</b>	
TITLE OF INVENTION <b>ANTISTATIC POLYMER COMPOSITION AND MOLDINGS THEREOF</b>					
APPLICANT(S) FOR DO/EO/US <b>KOBAYASHI, Toshikazu</b>					
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information					
1.	<input checked="" type="checkbox"/>	This is a <b>FIRST</b> submission of items concerning a filing under 35 U.S.C. 371.			
2.	<input type="checkbox"/>	This is a <b>SECOND</b> or <b>SUBSEQUENT</b> submission of items concerning a filing under 35 U.S.C. 371.			
3.	<input checked="" type="checkbox"/>	This is an express request to being national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b)) and PCT Articles 22 and 39(1).			
4.	<input checked="" type="checkbox"/>	A proper Demand for International Preliminary Examination was made by the 19 <sup>th</sup> month from the earliest claimed priority date.			
5.	<input checked="" type="checkbox"/>	A copy of the International Application was filed (35 U.S.C. 371 (c) (2))			
	a.	<input checked="" type="checkbox"/>	is transmitted herewith (required only if not transmitted by the International Bureau.		
	b.	<input type="checkbox"/>	has been transmitted by the International Bureau.		
	c.	<input type="checkbox"/>	is not required, as the application was filed in the United States Receiving Office (RO/US)		
6.	<input type="checkbox"/>	A translation of the International Application into English (35 U.S.C. 371 (c) (2)).			
7.	<input checked="" type="checkbox"/>	A copy of the International Search Report (PCT/ISA/210).			
8.	<input checked="" type="checkbox"/>	Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c) (3))			
	a.	<input checked="" type="checkbox"/>	are transmitted herewith (required only if not transmitted by the International Bureau).		
	b.	<input type="checkbox"/>	have been transmitted by the International Bureau.		
	c.	<input type="checkbox"/>	have not been made; however, the time limit for making such amendments has NOT expired.		
	d.	<input type="checkbox"/>	have not been made and will not be made.		
9.	<input type="checkbox"/>	A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371 (c)(3)).			
10.	<input checked="" type="checkbox"/>	An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).			
11.	<input checked="" type="checkbox"/>	A copy of the International Preliminary Examination Report (PCT/IPEA/409)			
12.	<input type="checkbox"/>	A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).			
<b>Items 13 to 18 below concern document(s) or information included :</b>					
13.	<input type="checkbox"/>	An Information Disclosure Statement under 37 CFR 1.97 and 1.98.			
14.	<input checked="" type="checkbox"/>	An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.			
15.	<input type="checkbox"/>	A FIRST preliminary amendment. A SECOND or SUBSEQUENT preliminary amendment.			
16.	<input type="checkbox"/>	A substitute specification.			
17.	<input checked="" type="checkbox"/>	A change of power of attorney and/or address letter.			
18.	<input checked="" type="checkbox"/>	Certificate of Mailing by Express Mail.			
19.	<input type="checkbox"/>	Other items or information:			
<b>17. General Power of Attorney</b> <b>18. Express Mailing Label No. EL031052714US</b>					

APPLICATION NO. (IF KNOWN, SEE 37 CFR) <b>09/582483</b>			INTERNATIONAL APPLICATION NO. <b>PCT/US98/27428</b>			ATTORNEY'S DOCKET NUMBER <b>AD-6547-A</b>	
<b>20.</b> The following fees are submitted						<b>CALCULATIONS PTO USE ONLY</b>	
<b>BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :</b>							
<input checked="" type="checkbox"/>	Search Report has been prepared by the EPO or JPO .....				<b>\$840.00</b>		
<input type="checkbox"/>	International preliminary examination fee paid to USPTO (37 CFR 1.482) .....				<b>\$670.00</b>		
<input type="checkbox"/>	No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37 CFR 1.445(a)(2)) .....				<b>\$760.00</b>		
<input type="checkbox"/>	Neither international preliminary examination fee paid to USPTO (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO .....				<b>\$970.00</b>		
<input type="checkbox"/>	International preliminary examination fee paid to USPTO (37 CFR 1.482)						
And all claims satisfied provisions of PCT Article 33(2)-(4)						<b>\$ 96.00</b>	
<b>ENTER APPROPRIATE BASIC FEE AMOUNT =</b>						<b>\$840.00</b>	
Surcharge of <b>\$130.00</b> for furnishing the oath or declaration later than months from the earliest claimed priority date (37 CFR 1.492 (e)). <input type="checkbox"/> 20 <input type="checkbox"/> 30						<b>\$0.00</b>	
<b>CLAIMS</b>	<b>NUMBER FILED</b>	<b>NUMBER EXTRA</b>	<b>RATE</b>				
Total Claims	<b>10     - 20     =</b>	<b>0               x</b>	<b>\$18.00</b>		<b>\$0.00</b>		
Independent Claims	<b>3          - 3          =</b>	<b>0               x</b>	<b>\$78.00</b>		<b>\$0.00</b>		
Multiple Dependent Claims ( <b>check if applicable</b> )			<input type="checkbox"/>		<b>\$0.00</b>		
<b>TOTAL OF ABOVE CALCULATIONS =</b>						<b>\$0.00</b>	
Reduction of ½ for filing by small entity, if applicable. Verified Small Entity Statement must also be filed (Note 37 CFR 1.9, 1.27, 1.28) ( <b>check if applicable</b> ). <input type="checkbox"/>						<b>\$0.00</b>	
<b>SUBTOTAL =</b>						<b>\$0.00</b>	
Processing Fee of <b>\$130.00</b> for furnishing the English translation later than months from the earliest claimed priority date (37 CFR 1.492 (f)). <input type="checkbox"/> 20 <input checked="" type="checkbox"/> 30						<b>\$0.00</b>	
<b>TOTAL NATIONAL FEE =</b>						<b>\$840.00</b>	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) ( <b>check if applicable</b> ). <input checked="" type="checkbox"/>						<b>\$40.00</b>	
<b>TOTAL FEES ENCLOSED =</b>						<b>\$880.00</b>	
						Amount to be : refunded	<b>\$</b>
						Charged	<b>\$</b>
<input type="checkbox"/> A check in the amount of _____ to cover the above fees enclosed. <input checked="" type="checkbox"/> Please charge my Deposit Account No. <b>04-1928</b> in the amount of <b>\$880.00</b> to cover the above fees. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any fees which may be required, or credit any overpayment to Deposit Account No. <b>04-1928</b> a duplicate copy of this sheet is enclosed.							
<b>NOTE : Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (CFR 1.37(a) or (b)) must be filed and granted to restore the application to pending status.</b>							
<b>SEND ALL CORRESPONDENCE TO:</b>							
<b>J. KENNETH JOUNG</b> <b>E. I. DU PONT DE NEMOURS AND COMPANY</b> <b>LEGAL PATENT RECORDS CENTER</b> <b>1007 MARKET STREET</b> <b>WILMINGTON, DELAWARE 19898</b> <b>UNITED STATES OF AMERICA</b>				<p style="margin-top: 20px; margin-bottom: 0;"><i>Andrew L. Schaeffer</i> Reg. No. 33,605</p> <hr/> SIGNATURE Andrew L. Schaeffer - for <b>J. KENNETH JOUNG</b> <hr/> NAME <div style="text-align: right; width: 150px;"><b>41,881</b></div> <hr/> REGISTRATION NUMBER <b>June 20, 2000</b> <hr/> DATE June 20, 2000			

09/582483  
532 Rec'd PCT/PTC 21 JUN 2000

PATENT COOPERATION TREATY

IN RE APPLICATION OF: E. I. DU PONT DE NEMOURS AND COMPANY  
INTERNATIONAL APPLICATION NO: PCT/US 98/27428  
FILED: December 23, 1998  
DUPONT CASE NO.: AD-6547-A  
TITLE: External Fixation Device

LETTER ACCOMPANYING AMENDMENT UNDER PCT ARTICLE 19

Fax: 41-22 740 14 35  
INTERNATIONAL BUREAU OF WIPO  
34, Chemin des Colombettes  
1211 Geneva 20  
Switzerland

Transmitted herewith are replacement sheets for the sheets of claims of the above-referenced international application as originally filed. The following indicates the differences between the claims as filed and as amended:

IN THE CLAIMS:

In claims 1, 2, 3, 4, 8, delete "polyether-system ion-conducting" and replaced by -- ion-conductive polyether-based polymer --. Support for the amendment can be found on page 10.

In claim 1, delete "bonded" from line 11 of page 22. In claim 8, delete "bonded" from line 22 of page 23.

In claims 1 and 8, add the followings to the group consisting of (page 22 and page 23): "and (ii) a source of at least one metal ion that is selected from the group consisting of sodium ion, potassium ion, ammonium ion, lithium ion, magnesium ion, calcium ion, copper ion, and zinc ion and that can react with the carboxyl groups or sulfo group of (i)"

Acceptance of this Amendment is respectfully requested.

Please acknowledge receipt of this Amendment by stamping and returning a copy of this letter which is enclosed.

Respectfully submitted,



Hanh T. Pham  
Attorney for Applicants

DuPont Legal  
BMP 17/1172  
Wilmington, DE 19898  
Tel. 302-992-4929

Date: 11 June 99

## ANTISTATIC POLYMER COMPOSITION AND MOLDINGS THEREOF

### Field of the Invention

The present invention relates to an antistatic polymer composition used to  
5 mold parts for which an antistatic effect is demanded, such as the transfer  
medium-separating guide parts of electrophotographic devices such as copiers and  
laser printers, which are placed at specific locations to guide the transfer medium,  
e.g., paper or polyester film, to which the electrostatic latent image is transferred,  
from the light-sensitive drum to the transfer zone and also to the fixing roller and  
10 to convey it from the device. More specifically, it relates to an antistatic polymer  
composition that can maintain its antistatic effect permanently due to the  
combination of an ion-conducting polymer, an ion source, and a plasticizer of the  
ion-conducting polymer, and also to moldings thereof.

### Background of the Invention

15 Polymers such as polyesters and polyamides are widely used in various  
fields such as packaging materials, electrical/electronic parts, and automotive  
parts. However, the moldings are likely to become charged electrostatically, so  
they cause static electricity problems. For example, the transfer medium-  
separating guide parts placed at specific locations in electrophotographic devices  
20 such as copiers and laser printers cause paper jams when the paper becomes  
difficult to separate because of static electricity.

In the past, a low-molecular-weight antistatic agent composed mainly of  
surfactant was incorporated into the polymer at the molding process or applied to  
the molding's surface in a finishing process in order to control the surface specific  
25 resistance of the molding to  $10^{13}$ - $10^8\Omega$ . However, the antistatic effect of  
surfactants is brought about by the equilibrium moisture adsorbed on the  
surfactant, so a sufficient antistatic effect was not manifested under low humidity.  
Also, the surfactant is removed by rubbing back and forth or washing, and the  
antistatic effect disappears.

30 Hence, polymers in which conductive materials such as conductive carbon  
fibers or metal fibers are incorporated as filler, polymers in which hydrophilic or

conductive monomers are incorporated by copolymerization to lower the electrical resistance of the polymer itself, and polymers rendered antistatic by alloying a hydrophilic polymer in the polymer have been developed. Also, various antistatic agents such as polyether systems, quaternary ammonium salt systems, sulfonic acid systems, and betaine systems have been introduced as permanent antistatic agents for addition to polymers (*Plastics Age*, Nov. 1993, published by Plastics Age Co.).

Specific examples of antistatic polyester compositions include an antistatic polymer composition obtained by compounding a thermoplastic resin with at least one polyoxyalkylene glycol or derivative thereof, a monomer unit comprising a vinyl-system unsaturated sulfonic acid or salt thereof, and a vinyl-system polymer to which an unsaturated aliphatic carboxylic acid alkyl ester with an alkyl group having 1-15 carbon atoms is bonded (Japanese Patent Application Kokai Publication Sho 60-202150); a polyester film with an antistatic effect obtained by compounding polyethylene terephthalate with a polyethylene glycol having a weight-average molecular weight of 4,000 to 50,000, an alkali metal salt of an alkylsulfonic acid, and an alkali metal salt of alkylbenzenesulfonic acid (Japanese Patent Application Publication Hei 2-232257); a polymer mixture containing polyester and a copolyetherester block copolymer with a polyether block derived from poly(propylene oxide) glycol having an ethylene oxide content of 15-35 wt% and a number-average molecular weight of 1,500 to 3,000 and capped with ethylene oxide (Japanese Patent Application Kokoku Publication Hei 7-110918); a composition with a permanent antistatic effect comprising polyetherester obtained by polycondensation of an aromatic dicarboxylic acid with 6-20 carbon atoms and/or ester thereof, poly(alkylene oxide) glycol having a number-average molecular weight of 200-50,000, and a glycol with 2-8 carbon atoms and a polycarbonate resin (Japanese Patent Application Kokai Publication Hei 8-245869); a thermoplastic resin composition obtained by compounding an aromatic polycarbonate resin, a block copolyamide resin, an impact modifier, phosphorus-containing compound with a spiro ring structure, and a metal deactivator (Japanese Patent Application Kokai Publication Hei 9-12854); and a permanent

antistatic resin composition comprising a polyetherester composed of a *para*-oriented aromatic dicarboxylic acid component with 4-20 carbon atoms, a specific aromatic diol component ring-substituted with a sulfonate salt group, a glycol component of 2-10 carbon atoms, and a poly(alkylene oxide) component with a number average molecular weight of 200-50,000 and having two ester-forming functional groups in its molecules, and a thermoplastic resin such as ABS (Japanese Patent Application Kokai Publication Hei 9-176497). However, the development of polymer compositions that can manifest a more uniform antistatic effect in the molding's surface is desired.

#### Problems this invention is to solve

The problem addressed by this invention is to provide an antistatic polymer composition that makes it possible for moldings to manifest a uniform antistatic effect permanently with little change in surface resistance owing to humidity. More specifically, the problem addressed by this invention is to provide an antistatic polymer composition that is ideally used for polymer moldings where static electricity is a problem, such as the transfer medium-separating guide parts placed at specific locations in electrophotographic devices.

Another object is to provide a polymer composition giving further water-repellency with maintaining excellent antistatic effect by reducing changes in surface resistivity of molded article therefrom, which is useful in moldings requiring both antistatic effect and water-repellency.

#### Summary of the Invention

As a result of studies to solve such problems, the present inventors discovered that an outstanding antistatic effect can be provided by compounding an ion-conducting polymer, an ion source or electrolyte, and a plasticizer of the ion-conducting polymer in the matrix polymer. That is, the antistatic polymer composition according to the first of these inventions is characterized in that it contains

(A) one or more polymers selected from the group consisting of polyester, polycarbonate, polyamide, polyoxymethylene, polyphenylene sulfide, and compounds of polyphenylene oxide and polystyrene;


(B) a polyether-system ion-conducting polymer;

(C) an ion source comprising (i) a source of at least one carboxyl group or sulfo group selected from the group consisting of hydrocarbon acids containing 6-54 carbon atoms, sulfonic acids and organic polymers with at least one bonded carboxyl group or sulfo group and (ii) a source of at least one metal ion that is selected from the group consisting of sodium ion, potassium ion, lithium ion, magnesium ion, and zinc ion and that can react with the carboxyl group or sulfo group of (i), solid electrolytes or polymer electrolytes ; and

(D) a plasticizer of the aforementioned polyether-system ion-conducting polymer (B).

The antistatic polymer composition that is the second invention is characterized in that the above-indicated polyether-system ion-conducting polymer is polyetherester amide.

The third invention is the antistatic polymer composition of the aforementioned item (1) or (2) characterized in that the aforementioned plasticizer (D) is a plasticizer represented by formula (1):



(wherein m is an integer of 1-3, n is an integer of 4-25, A is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, B is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, and X is H, CH<sub>3</sub>, or C<sub>2</sub>H<sub>5</sub>).

The fourth invention is the antistatic polymer composition of any one of the aforementioned item(1) to (3) characterized in that it contains 40.0-98.4 wt% of polymer (A), 1.0-35.0 wt% of polyether-system ion-conducting polymer (B), 0.1-15.0 wt% of ion source (C), and 0.5-10.0 wt% of plasticizer (D) with respect to the weight of the composition as a whole.

The fifth invention is the antistatic polymer composition characterized in comprising:

(A) one or more polymers selected from the group consisting of ABS (acrylonitrile butadiene styrene), polyethylene, polypropylene, polypropylene copolymer and EPDM (ethylene/propylene/diene) elastomer;

(B) a polyether-system ion-conducting polymer;

(C) an ion source comprising (i) a source of at least one carboxyl group or sulfo group being selected from the group consisting of hydrocarbon acids containing 6-54 carbon atoms, sulfonic acids and organic polymers with at least one bonded carboxyl group or sulfo group and (ii) a source of at least one metal ion that is selected from the group consisting of sodium ion, potassium ion, lithium ion, magnesium ion, and zinc ion and that can react with the carboxyl groups or sulfo group of (i), solid electrolytes or polymer electrolytes; and (D) a plasticizer of the aforementioned polyether-system ion-conducting polymer

10 (B).

The sixth invention is the antistatic polymer composition of any one of the aforementioned item(1) to (5) characterized in further comprising a water-repellent comprising fluorinated compounds, silicone compounds or a mixture thereof.

15 Still another invention is moldings such as the transfer medium-separating guide parts for electrophotographic devices and any molded items requiring antistatic effect and water-repellency characterized in that they are molded from the above antistatic polymer composition.

20

#### Detailed Description of the Invention

The antistatic polymer composition of this invention has antistatic properties of at least a degree that can control the surface specific resistance of moldings to  $10^{13}$ - $10^8 \Omega$ .

25 Polymer (A) of this invention is one or more polymers selected from the group consisting of polyester, polycarbonate, polyamide, polyoxymethylene, polyphenylene sulfide, and compounds of polyphenylene oxide and polystyrene.

The polyester is polyethylene terephthalate obtained by polycondensation of ethylene glycol and terephthalic acid, polybutylene terephthalate obtained by polycondensation of butanediol and terephthalic acid, or a copolymer of ethylene terephthalate or polybutylene terephthalate that contains another comonomer component in a range that provides physical or chemical properties. As

30



comonomer components used in manufacturing the copolymer, ethylene glycol, 1,2-propylene glycol, pentanediol, hexanediol, 1,4-cyclohexanedimethanol, and the like can be mentioned as the glycol component and isophthalic acid and naphthalenedicarboxylic acid can be mentioned as the dicarboxylic acid component.

The intrinsic viscosity of the polyester is 0.3-1.3, preferably 0.5-1.0, more preferably 0.6-0.9.

The polyesters ideally used in this invention are polyethylene terephthalate, polybutylene terephthalate, and compounds of these.

In addition, the polyesters of this invention also include melt-processible polyesters or polyester amides that can form an anisotropic molten phase, generally called thermotropic liquid crystal polymers. The constituents of such polymers are aromatic hydroxycarboxylic acids, aromatic dicarboxylic acids, aliphatic dicarboxylic acids, aromatic diols, aliphatic diols, aromatic hydroxylamines, and aromatic diamines. The melt-processible polyesters or polyester amides that can form an anisotropic molten phase are obtained by polymerizing one of these constituents or by copolymerizing two or more of these constituents.

The following specific examples can be mentioned: aromatic polyesters obtained by polymerizing one or more aromatic hydroxycarboxylic acids; aromatic polyesters obtained by polymerizing an aromatic dicarboxylic acid, one or more aliphatic dicarboxylic acid, an aromatic diol, and one or more aliphatic diols; aromatic polyesters obtained by polymerizing an aromatic hydroxycarboxylic acid as the main component and one or more components selected from the group consisting of aromatic dicarboxylic acids, aliphatic dicarboxylic acids, aromatic diols, and aliphatic diols; aromatic polyester amides obtained by polymerizing an aromatic hydroxylamine, one or more aromatic diamines, and one or more aromatic hydroxycarboxylic acids; aromatic polyester amides obtained by polymerizing an aromatic hydroxylamine, one or more aromatic diamines, one or more aromatic hydroxycarboxylic acids, an aromatic dicarboxylic acid, and one or more aliphatic carboxylic acid; and aromatic

polyester amides obtained by polymerizing an aromatic hydroxylamine, one or more aromatic diamines, one or more aromatic hydroxycarboxylic acids, an aromatic dicarboxylic acid, one or more aliphatic carboxylic acids, an aromatic diol, and one or more aliphatic diols.

- 5           As examples of aromatic hydroxycarboxylic acids, 4-hydroxybenzoic acid, 3-hydroxybenzoic acid, 2-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, and 5-hydroxy-2-naphthoic acid, and hydroxybenzoic acids substituted with halogens, alkyls, and aryls can be mentioned.

- As aromatic dicarboxylic acids, terephthalic acid, isophthalic acid, 3,3N-  
10   diphenyldicarboxylic acid, 4,4 N -diphenyldicarboxylic acid, 1,4-naphthalenedicarboxylic acid, 1,5-naphthalenedicarboxylic acid, 2,6-naphthalenedicarboxylic acid, and alkyl- and halogen-substituted aromatic dicarboxylic acids such as *tert*-butylterephthalic acid and chloroterephthalic acid can be mentioned.

- 15           As aliphatic dicarboxylic acids, cyclic aliphatic dicarboxylic acids such as *trans*-1,4-cyclohexanedicarboxylic acid, *cis*-1,4-cyclohexanedicarboxylic acid, and 1,3-cyclohexanedicarboxylic acid and substituted derivatives of these can be mentioned.

- As aromatic diols, the following can be mentioned: hydroquinone,  
20   diphenol, 4,4 N -dihydroxydiphenyl ether, 3,4 N -dihydroxydiphenyl ether, bisphenol A, 3,4 N -dihydroxydiphenylmethane, 3,3 N -dihydroxydiphenylmethane, 4,4 N -dihydroxydiphenylsulfone, 3,4 N -dihydroxydiphenylsulfone, 4,4 N -dihydroxydiphenyl sulfide, 3,4 N -dihydroxydiphenyl sulfide, 2,6 N -naphthalenediol, 1,6 N -naphthalenediol, 4,4 N -  
25   dihydroxybenzophenone, 3,4 N -dihydroxybenzophenone, 3,3 N -dihydroxybenzophenone, 4,4 N -dihydroxydiphenyldimethylsilane, and alkyl- and halogen-substituted derivatives of these.

- As examples of aliphatic diols, cyclic, linear, and branched aliphatic diols such as *trans*-1,4-hexanediol, *cis*-1,4-hexanediol, *trans*-1,3-cyclohexanediol, *cis*-  
30   1,2-cyclohexanediol, ethylene glycol, 1,4-butanediol, 1,6-hexanediol, 1,8-octanediol, *trans*-1,4-cyclohexanedimethanol, *cis*-1,4-cyclohexanedimethanol, and

*cis*-1,4-cyclohexanedimethanol and substituted derivatives of these can be mentioned.

As examples of aromatic hydroxylamines and aromatic diamines, 4-aminophenol, 3-aminophenol, *p*-phenylenediamine, and *m*-phenylenediamine, and substituted derivatives of these can be mentioned.

The liquid crystal polymers used in this invention generally have a number-average molecular weight of approximately 2,000-200,000, preferably 5,000-50,000, and more preferably 10,000-20,000.

The liquid crystal polymers ideally used in this invention are copolymers of 4-hydroxybenzoic acid and 6-hydroxy-2-naphthoic acid and copolymers of hydroquinone, diphenol, terephthalic acid, 2,6-naphthalenedicarboxylic acid, 4-hydroxybenzoic acid, and 6-hydroxy-2-naphthoic acid.

The polyamide that is another matrix polymer of this invention is obtained by polycondensation of a diamine component and a dicarboxylic acid component. As examples, polyamides obtained by polymerizing one or more diamines selected from the group consisting of aliphatic alkylenediamines, aromatic diamines, and alicyclic diamines and one or more dicarboxylic acid selected from the group consisting of aliphatic dicarboxylic acids, aromatic dicarboxylic acids, and aliphatic aminocarboxylic acids, and compounds of these can be mentioned.

The aliphatic alkylenediamine may be linear or branched. As specific examples, ethylenediamine, trimethylenediamine, tetramethylenediamine, pentamethylenediamine, hexamethylenediamine, 1,7-diaminoheptane, 1,8-diaminooctane, 1,9-diaminononane, 1,10-diaminodecane, 2-methylpentamethylenediamine, and 2-ethyltetramethylenediamine can be mentioned. These aliphatic alkylenediamines can be used alone, or two or more can be used combined.

The aromatic diamines may be used alone, or two or more may be used combined. As an example, *p*-phenylenediamine, *o*-phenylenediamine, *m*-phenylenediamine, *p*-xylenediamine, and *m*-xylenediamine can be mentioned.

As specific examples of alicyclic alkylenediamines, 1,3-diaminocyclohexane, 1,4-diaminocyclohexane, 1,3-bis(aminomethyl)cyclohexane,

bis(aminomethyl)cyclohexane, bis(4-aminocyclohexyl)methane, 4,4N -diamino-3,3N -dimethyldicyclohexylmethane, isophoronediamine, and piperazine can be mentioned. These can be used alone, or two or more can be used combined.

As aliphatic dicarboxylic acids, adipic acid, sebacic acid, azelaic acid, and dodecanedioic acid can be mentioned. These can be used alone, or two or more can be used combined.

As examples of aromatic dicarboxylic acids, terephthalic acid, isophthalic acid, phthalic acid, 2-methylterephthalic acid, and naphthalenedicarboxylic acid can be mentioned, and as an example of aromatic aminocarboxylic acids, *p*-aminobenzoic acid can be mentioned. These aromatic monomers can be used alone, or two or more can be used combined.

As specific examples of aminocarboxylic acids,  $\epsilon$ -aminocaproic acid and  $\gamma$ -aminoundecanoic acid can be mentioned. These can be used alone, or two or more can be used combined.

Also, the number-average molecular weight of the polyamide is 2,000-50,000, preferably 5,000-40,000, and still more preferably 7,000-30,000.

The polyamides ideally used in this invention are nylon 66, nylon 6, copolymer of nylon 66 and nylon 6, and compounds of these.

Polycarbonates are obtained by the ester-exchange method, which reacts bisphenol A with diphenyl carbonate in a molten state, and by the solution polycondensation method, which reacts bisphenol A with phosgene in pyridine as solvent and acid-acceptor.

The number-average molecular weight of the polycarbonate is 6,000-100,000, preferably 10,000-80,000, and still more preferably 15,000-50,000.

Polyoxymethylene homopolymer is obtained by polymerization of formaldehyde, and copolymer is obtained by polymerization of trioxane with a cyclic ether or cyclic formal.

The number-average molecular weight of polyoxymethylene is 8,000-150,000, preferably 12,000-100,000, and still more preferably 20,000-80,000 for both homopolymer and copolymer.

Polyphenylene sulfide is obtained by reacting *p*-dichlorobenzene and

sodium sulfide in a polar solvent such as *N*-methylpyrrolidone at a high temperature of 200°C or above.

The weight-average molecular weight of polyphenylene sulfide is 5,000-90,000, preferably 8,000-70,000, and still more preferably 10,000-60,000.

5 With respect to compounds of polyphenylene oxide and polystyrene, polyphenylene oxide and polystyrene have the property of mutually dissolving completely in all ratios, so they may be mixed in any ratio.

The compound of polyphenylene oxide and polystyrene ideally used in this invention is a compound for which the weight ratio of polyphenylene oxide to  
10 polystyrene is 70:30 to 50:50.

Other suitable matrix polymers of the present invention may be, for example, ABS (acrylonitrile butadiene styrene), polyethylene, polypropylene, polypropylene copolymer and EPDM(ethylene/propylene/diene) elastomer.

Ion-conducting polymer (B) used in this invention is a polyether-system  
15 ion-conducting polymer. Polyethers have good compatibility with the matrix polymers, polyester and polyamide, so a uniform antistatic effect can be provided to the surface of moldings.

As specific examples, polyethylene oxide, polyetherester amide, polyetheramideimide, ethylene oxide-epihalohydrin copolymer, and  
20 methoxypolyethylene glycol (meth)acrylate copolymer can be mentioned. Polyethers of low degree of crystallization are preferred, and polyetherester amides are especially preferred.

The content of the polyether-system ion-conducting polymer is 1.0-35.0 wt%, preferably 3.0-20.0 wt%, and still more preferably 4.5-12.5 wt%, with  
25 respect to the weight of the composition. If less than 1.0 wt%, the antistatic effect will be insufficient, and if more than 35.0 wt%, this will lead to a decline in mechanical properties.

Ion source (C) used in this invention comprises

(i) a source of at least one carboxyl group or sulfo group selected from the  
30 group composed of hydrocarbon acids with 6-54 carbon atoms, sulfonic acids and organic polymers with at least one bonded carboxyl group or sulfo group and

(ii) a source of at least one metal ion that is selected from the group composed of sodium ion, potassium ion, lithium ion, magnesium ion, and zinc ion and that can react with the carboxyl groups or sulfo group of (i), solid electrolytes or polymer electrolytes.

5 Solid electrolytes or polymer electrolytes are used instead of the ion source comprising the source of carboxyl group or sulfo group defined (i) and metal ion source defined (ii) in the antistatic polymer composition of this invention according to the intended application of use. Examples of the solid electrolytes include chemical composition which is expressed by XY or XW<sub>2</sub> wherein X is  
10 Li, Na, K, or NH<sub>4</sub>, Y is ClO<sub>4</sub>, I, BF<sub>4</sub>, or CF<sub>3</sub>SO<sub>3</sub> and W is Mg, Ca, Zn, or Cu.

In addition, polymer electrolytes capable of being used in this invention represent a wide range of compositions that can, for example, be polystyrenesulfonic acid sodium salt and acrylate copolymer ammonium salt.

By including the ion source, ions can be sufficiently supplied to the  
15 aforementioned ion-conducting polymer, so the ion-conducting polymer can sufficiently manifest an antistatic effect.

Preferably, carboxyl-group or sulfo group source (i) is a source of at least one carboxyl group or sulfo group [selected from the group] consisting of hydrocarbon acids containing 7-25 carbon atoms, sulfonic acids and organic  
20 polymers that contain pendant carboxyl groups or sulfo groups.


More preferably, ionomers composed of organic ionic hydrocarbon copolymers of  $\alpha$ -olefins with 2-5 carbon atoms and  $\alpha$ ,  $\beta$ -ethylenically unsaturated carboxylic acids with 3-5 carbon atoms whose carboxyl groups are at least partially neutralized with sodium or potassium cations are ideally used.

25 Other suitable ionomers contain (i) polyethylene terephthalate and/or polybutylene terephthalate oligomer and (ii) a substance derived from a sodium and/or potassium ion source that can react with the oligomer-like carboxyl end groups of (i).

The content of the ion source is 0.1-15.0 wt%, preferably 0.3-12.0 wt%,  
30 more preferably 1.0-8.0 wt%, with respect to the weight of the composition. If less than 0.1 wt%, the antistatic effect will be insufficient, and if more than 15.0 wt%,

this will lead to a decline in mechanical properties. The ion source contains a sufficient amount of the metal ion source that the concentration of metal in the composition will be greater than 1.0 wt%.

Plasticizer (D) used in this invention has a plasticizing effect on the polyether-system ion-conducting polymer used. As specific examples, phthalate ester plasticizers such as dimethyl phthalate, dibutyl phthalate, butyl benzyl phthalate, and di-2-ethylhexyl phthalate, phosphate ester plasticizers such as tricresyl phosphate and triphenyl phosphate, sulfonamide plasticizers such as *o,p*-toluenesulfonamide, *N*-ethyl-*o,p*-toluenesulfonamide, *N*-methylbenzenesulfonamide, *N*-ethylbenzenesulfonamide, and *N*-butylbenzenesulfonamide, and polyether system plasticizers can be mentioned. The preferred plasticizer is represented by formula (1):



wherein *m* is an integer of 1-3, *n* is an integer of 4-25, A is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, B is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, and X is H, CH<sub>3</sub>, or C<sub>2</sub>H<sub>5</sub>.

Because the composition of this invention contains a plasticizer, the ions can easily move under high-temperature conditions, so the higher the temperature at which the molding is used, the more outstanding the antistatic effect that can be manifested.

The preferred plasticizer is obtained when *m* is 1, or *n* is 4-14, or X is H, and especially when *m* is 1, *n* is 4-14, and also X is H. The more preferred plasticizer is obtained when *m* is 1, or *n* is 7-13, or X is H, or A is an acyl with 8 carbon atoms or methyl, or B is an acyl with 8 carbon atoms, and especially when *m* is 1, *n* is 7-13, X is H, A is an acyl with 8 carbon atoms or methyl, and B is an acyl with 8 carbon atoms.

The preferred specific examples are polyethylene glycol 400 bis(2-ethylhexanoate), methoxypolyethylene glycol 550 2-ethylhexanoate, and tetraethylene glycol bis(2-ethylhexanoate). Of these, polyethylene glycol 400 bis(2-ethylhexanoate) is most ideally used.

The amount of plasticizer contained is 0.5-10.0 wt%, preferably 1.0-8.0 wt%, and still more preferably 2.0-6.0 wt% with respect to the weight of the composition. If less than 0.5 wt%, the antistatic effect will not be sufficient, and if more than 10.0 wt%, this will lead to a decline in mechanical properties.

5 Well-known flame retardants can be mixed in the composition of this invention. Specifically, brominated flame retardants such as polydibromostyrene, polytribromostyrene, polypentabromostyrene, decabromodiphenyl, tetrabromodiphenyl, hexabromodiphenyl ether, octabromodiphenyl ether, decabromodiphenyl ether, tetrabromodiphenyl sulfide, polypentabromobenzyl  
10 acrylate, brominated phenoxy resin, and epoxy-terminated phenoxy resin [sic] can be mentioned. Epoxy-terminated phenoxy resin [sic] and brominated polystyrene are preferred. The loading of flame retardant is usually 7-20 wt% based on the weight of the composition.

Along with the flame retardant, antimony compounds well known as  
15 flame-retarding assistants, such as antimony oxides and sodium antimonate, may be compounded.

Inorganic fillers commonly used to reinforce engineering plastics can also be compounded. As specific examples of inorganic fillers, glass fibers, carbon fibers, potassium titanate, whiskers, kaolin, clay, talc, wollastonite, calcium  
20 carbonate, silica, and mica can be mentioned. Glass fibers are ideally used. The loading of inorganic filler is usually 5-60 wt% based on the weight of the composition.

In addition to the above components, the composition of this invention may be compounded with commonly used additives such as impact modifiers,  
25 heat stabilizers, antioxidants, dyes, pigments, and release agents in ranges that do not impair its properties.

Also, it is possible to obtain a polymer giving significant improvements in both antistatic effect and water-repellency by adding any water-repellents, such as fluorinated compounds, silicone compounds or chemical compositions thereof that  
30 have low surface free energy and well know in the art, in appropriate amounts in addition to the aforementioned antistatic polymer composition of this invention.



When the water-repellent is used in combination with a low-molecular-weight antistatic agent composed mainly of surfactant incorporated into the polymer at the molding process or applied to the molding's surface in a finishing process, it may be able to improve sliding characteristics by reducing coefficient of kinetic friction, but can easily cause static electricity resulting into static electricity problem. Examples of the water-repellents are PTFE, PFA, FEP, ETFE, modified silicone such as silicone oil, silicone gum, amino-modified silicone and epoxy-modified silicone, fluorosilicone and perfluoroalkyl group containing oligomer.

The polymer composition of this invention can be manufactured by any well-known method used in the past. For example, it can be melt blended using the mixing devices generally used, such as the Banbury mixer, extruders, and various kneaders. With respect to the order of blending, all the components may be blended at the same time, or the ion-conducting polymer, ion source, and plasticizer may be fed from side feeders.

The composition of this invention can be used to manufacture moldings that are used in devices for which static electricity is a problem, such as the transfer medium-separating guide parts placed at specific locations in electrophotographic devices by a well-known method such as injection molding.

Also, it is possible to obtain products formed by molding the antistatic polymer composition of this invention, which has surface resistivity in the range of  $10^7$  to  $10^{13} \Omega$ , as measured according to test method of ASTM D 257 and is capable of being applied an electrostatic painting directly onto surface of the molded article without any primer. Since the molded articles made from the antistatic polymer composition of this invention don't require to be applied any surface treatment agent such as a solution in alcohol containing 0.5 to 1 % by weight of surfactant on the surface of the molded article to reduce its surface specific resistance by moisture absorption by the surfactant, the electrostatic painting may be used for the molded articles made from the antistatic polymer composition of this invention.

#### Practical examples

This invention will now be explained with practical examples, but it is not

limited to only these examples.

Practical Example 1, Comparative Examples 1-5

The components shown in Table 1 were melt blended with a twin-screw extruder (ZSK-40 manufactured by W&P). After water cooling, pellets were  
5 manufactured. The pellets obtained were used to mold test pieces (7.5 mm x 12.5 mm x 3 mm). The mold temperature and resin temperature when molding were 110°C and 290°C, respectively.

The test pieces obtained were used to determine surface resistivity and volume resistivity. The results are shown in Table 1. The methods of  
10 determination were as follow:

Method for determining surface resistivity: Based on ASTM D257

Method for determining volume resistivity: Based on ASTM D257

The components referred to in the tables are as follows:

Polymer: Polyethylene terephthalate with an intrinsic viscosity of 0.65  
15 (trade name Rynite manufactured by DuPont).

Ion-conducting polymer: Polyetherester amide copolymer (trade name Perestat 6321 manufactured by Sanyo Chemical Industries)

Ion source: Sodium-neutralized ethylene-methacrylic acid copolymer with 60% of the carboxylic acid of a copolymer composed of ethylene-methacrylic  
20 resin (weight ratio 85/15) neutralized with sodium (trade name Surlyn 8920 manufactured by DuPont)

Plasticizer: Polyethylene glycol 400 bis(2-ethylhexanoate) (trade name Rionon DEH-40 manufactured by Lion K.K.)

Glass fibers: PPG3540 chopped strand

Table 1

	PE 1*	CE 1*	CE 2	CE 3	CE 4	CE 5
polymer (wt%)	58.5	70.0	65.0	64.0	61.5	60.0
Ion-conducting polymer (wt%)	6.0	0	0	6.0	6.0	6.0
Ion source (wt%)	4.0	0	3.5	0	0	4.0
Plasticizer (wt%)	2.5	0	1.5	0	2.5	0
Glass fibers (wt%)	30.0	30.0	30.0	30.0	30.0	30.0
Surface resistivity $\Omega$	8.91 H $10^{12}$	1.94 H $10^{16}$	2.00 H $10^{17}$	2.24 H $10^{16}$	1.92 H $10^{14}$	5.40 H $10^{13}$
Volume resistivity ( $\Omega$ -cm)	1.45 H $10^{13}$	8.00 H $10^{15}$	1.30 H $10^{16}$	2.75 H $10^{15}$	2.95 H $10^{14}$	1.4 H $10^{14}$

\*PE = Practical Example CE = Comparative Example

When Practical Example 1 and Comparative Examples 1-5 were compared, the molding made from the composition of this invention had high surface specific resistance and volume specific resistance and was superior in antistatic effect.

When Comparative Example 3 and Comparative Example 4 were compared, it was found that the antistatic effect is improved by using a plasticizer along with the ion-conducting polymer, and when Comparative Example 3 and Comparative Example 5 were compared, it was found that the antistatic effect is also improved by using an ion source along with the ion-conducting polymer. However, neither case showed improvement in antistatic effect to the extent of Practical Example 1, in which both a plasticizer and an ion source were used along with the ion-conducting polymer.

#### Practical Examples 2-5, Comparative Examples 6-9

Test pieces were molded using a composition comprising 41.0 wt% of polyethylene terephthalate having an intrinsic viscosity of 0.65 (trade name Rynite manufactured by DuPont), 5.5 wt% of polyetherester amide copolymer (trade name Perestat 6321 manufactured by Sanyo Chemical Industry), 3.5 wt% of ethylene-methacrylic acid copolymer neutralized with sodium (trade name Surlyn 8920 manufactured by DuPont), 1.5 wt% of polyethylene glycol 400 bis(2-ethyl-hexanoate) (trade name Rionon DEH-40 manufactured by Lion K.K.), 13.0 wt% of polytribromostyrene (Pyro-chek 68 manufactured by Nissan Ferro), 0.5 wt% of antimony trioxide, and 35.0 wt% of glass fibers (PPG3540 chopped strand) for the

practical examples.

Test pieces were molded using a composition comprising 99.0 wt% of polyethylene terephthalate having an intrinsic viscosity of 0.65 (trade name Rynite manufactured by DuPont) and 1.0 wt% of sodium alkylsulfonate as the

5 comparative examples.

The test pieces obtained were used to test the effects of temperature and humidity on surface specific resistance. The results of measurement at 25°C, 50°C, 80°C, and 120°C are shown in Tables 2, 3, 4, and 5, respectively.

Table 2

Temperature: 25°C

Humidity (%)	Surface resistivity ( $\Sigma$ )	
	Practical Example 2	Comparative Example 6
10	$3.66 \text{ H } 10^{11}$	$1.19 \text{ H } 10^{16}$
30	$1.59 \text{ H } 10^{10}$	--
50	$1.17 \text{ H } 10^{10}$	$7.56 \text{ H } 10^{10}$
70	$2.77 \text{ H } 10^{10}$	--
95	$1.43 \text{ H } 10^{10}$	$1.35 \text{ H } 10^{10}$

Table 3

Temperature: 50°C

Humidity (%)	Surface resistivity ( $\Sigma$ )	
	Practical Example 3	Comparative Example 7
10	$7.75 \text{ H } 10^9$	$4.86 \text{ H } 10^{14}$
30	$3.58 \text{ H } 10^9$	--
50	$1.71 \text{ H } 10^9$	$3.65 \text{ H } 10^9$
70	$7.83 \text{ H } 10^8$	--
95	$5.81 \text{ H } 10^7$	$3.92 \text{ H } 10^8$

Table 4

Temperature: 80°C

Humidity (%)	Surface resistivity ( $\Sigma$ )	
	Practical Example 4	Comparative Example 8
10	$1.12 \text{ H } 10^9$	$2.97 \text{ H } 10^{14}$
30	$4.98 \text{ H } 10^8$	--
50	$5.40 \text{ H } 10^8$	$7.57 \text{ H } 10^{10}$
70	$1.44 \text{ H } 10^8$	--
95	$2.73 \text{ H } 10^7$	$1.30 \text{ H } 10^8$

Table 5

Temperature: 120°C

Humidity (%)	Surface resistivity ( $\Omega$ )	
	Practical Example 5	Comparative Example 9
10	$1.46 \text{ H } 10^9$	$5.67 \text{ H } 10^{12}$

5 Under any of the temperature conditions, the difference between the surface specific resistance of the practical examples and comparative examples became greater as the humidity became lower, and a difference arose in their antistatic effects. And even at the same humidity, the antistatic effect of the comparative examples declined as the temperature increased, but the antistatic effect of the practical examples increased as the temperature increased.

#### Practical Example 6 and Comparative Example 10

The same test pieces as in Practical Example 2 and Comparative Example 6, respectively, were used. To investigate durability of rubbing resistance, the surface was wiped with a cloth moistened with water or with a dry cloth, and surface specific resistivity was determined.

Table 6

Temperature: 25°C, humidity: 50%

Number of times wiped with damp cloth	Surface resistivity ( $\Sigma$ )	
	Practical Example 6	Comparative Example 10
0	$1.17 \text{ H } 10^{10}$	$7.56 \text{ H } 10^{10}$
1	$1.99 \text{ H } 10^{10}$	$1.59 \text{ H } 10^{15}$
5	$2.00 \text{ H } 10^{10}$	$3.24 \text{ H } 10^{14}$
Number of times wiped with dry cloth		
5	$1.15 \text{ H } 10^{10}$	$5.67 \text{ H } 10^{14}$

Whether wiped with a damp cloth or dry cloth, there was no change in the antistatic effect of moldings made from the composition of this invention, but when a surfactant was used as in the comparative example, rubbing caused the antistatic effect to decline.

#### Examples 7 - 11 and comparative examples 11 and 12

In addition to the matrix polymer, ion-conducting polymer, plasticizer and

glass fibers used in Example 1 and Comparative examples 1 - 5 summarized in Table 1, and additional various ion sources in amount, all as specified in Table 7. The results of surface and volume resistivities measured according to ASTM D257 are also given in Table 7.

5

Table 7

	PE 7*	PA 8*	PA 9	PA 10	PA 11	CE 11	CE12
polymer (wt%)	62	62	59.5	62.4	51.5	62.45	62.42
Ion-conducting polymer (wt%)	6.0	6.0	6.0	6.0	13	6.0	6.0
Ion source A (wt%)					4		0.08
Ion source B (wt%)	0.5					0.05	
Ion source C (wt%)		0.5					
Ion source D (wt%)			3				
Ion source E (wt%)				0.1			
Plasticizer (wt%)	1.5	1.5	1.5	1.5	1.5	1.5	1.5
Glass fibers (wt%)	30.0	30.0	30.0	30.0	30.0	30.0	30.0
Surface resistivity ( $\Omega$ )	$9.67 \times 10^{12}$	$1.26 \times 10^{13}$	$1.67 \times 10^{11}$	$8.62 \times 10^{11}$	$1.89 \times 10^9$	$5.51 \times 10^{14}$	$3.26 \times 10^{14}$
Volume resistivity ( $\Omega$ -cm)	$7.21 \times 10^{12}$	$8.26 \times 10^{12}$	$4.83 \times 10^{12}$	$2.28 \times 10^{11}$	$2.28 \times 10^8$	$1.89 \times 10^{14}$	$2.41 \times 10^{14}$

\*PE = Practical Example CE = Comparative Example

Ion source A: Sodium-neutralized ethylene-methacrylic acid copolymer with 60% of the carboxylic acid of a copolymer composed of ethylene-methacrylic resin (weight ratio 85/15) neutralized with sodium (trade name Surlyn 10 8920 manufactured by DuPont),

Ion source B: Sodium Montanate, commercially available under the tradename Hostamont NaV 101 from Clariant Japan, Inc.

Ion source C: Lithium Montanate, commercially available under the 15 tradename Hostmont LiV 103 from Clariant Japan, Inc.

Ion source D: Polystyrenesulfonic acid sodium salt,

Ion source E: Lithium Iodide

#### Examples 11 - 13 and Comparative examples 13 -18

To see the effect of adding water-repellents in addition to the antistatic 20 polymer composition of this invention, additional formulations of examples 11 - 13 and comparative examples 13 - 18 were prepared, as summarized in the following Table 8. Using water-repellent of fluorinated compounds or silicone

compounds instead of the surfactant, Examples 11 -13, is seen to provide both water-repellency maintaining and antistatic effect.

The results, as to whether or not water-repellency is improved, and the values of water-repellent angle measured by the commonly known test method,  
5 are also given in Table 8.

Table 8

	PE 11	PA12*	PA13	CE13	CE14	CE 15	CE16	CE17	CE18
polymer (wt%)	54.5	42.5	56	66	54	67.5	57.5	69	70
Ion-conducting polymer (wt%)	6.0	6.0	6.0				6.0		
Ion source (wt%)	4	4	4		4		4		
Water-repellent A (wt%)	3			3					
Water-repellent B (wt%)		15			15				
Water-repellent C (wt%)			1.5			1.5			
surfactant (wt%)				1	1	1		1	
Plasticizer (wt%)	2.5	2.5	2.5				2.5		
Glass fibers (wt%)	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0
Surface resistivity ( $\Omega$ )	5.22x 10 <sup>12</sup>	6.95x 10 <sup>12</sup>	4.88x 10 <sup>12</sup>	8.62x 10 <sup>11</sup>	2.76x 10 <sup>12</sup>	5.51x 10 <sup>14</sup>	8.91x 10 <sup>12</sup>	4.88x 10 <sup>12</sup>	4.88x 10 <sup>16</sup>
Water repellent angle (°)	107	103	109	49	38	46	58	32	68

\*PE = Pratical Example CE = Comparative Example

Water-repelent A: Silicone oil master batch, commercially available under  
10 the tradename BY27-009 from Toray Dow Silicone, Inc.

Water-repellent B: PTFE powder, commercially available under the tradename MP 1500 from DuPont,

Water-repellent C: Perfluoroalkyl acrylate-alkylacrylate block copolymer, commercially available under the tradename Megafac 178RM from DaiNippon  
15 Ink Co., Ltd.

Surfactant : Alkyl-benzene sulfonic acid sodium salt compound, commercially available under the tradename Chemistat 3033 from Sanyo Kasei Kogyo Inc.

Effects of the invention

According to this invention, it was possible to provide an antistatic polymer composition that is able to manifest a uniform antistatic effect permanently with little change in the surface resistance of moldings owing to  
5 humidity. The moldings molded from the polymer composition of this invention are ideally used in devices where static electricity is a problem.



Claims

What is claimed is:

1. An antistatic polymer composition characterized in that it comprises:

(A) one or more polymers selected from the group consisting of polyester, polycarbonate, polyamide, polyoxymethylene, polyphenylene sulfide, and compounds of polyphenylene oxide and polystyrene;


(B) a ion-conductive polyether-based polymer;

(C) an ion source comprising: (i) a source of at least one carboxyl group or sulfo group being selected from the group consisting of hydrocarbon acids containing 6-54 carbon atoms, sulfonic acids and organic polymers with at least one carboxyl group or sulfo group; and (ii) a source of at least one metal ion that is selected from the group consisting of sodium ion, potassium ion, ammonium ion, lithium ion, magnesium ion, calcium ion, copper ion, and zinc ion and that can react with the carboxyl groups or sulfo group of (i), solid electrolytes or polymer electrolytes; and

(D) a plasticizer of the aforementioned ion-conductive polyether-based polymer (B).

2. The antistatic polymer composition of Claim 1 characterized in that the ion-conductive polyether-based polymer (B) is a polyetherester amide.

3. The antistatic polymer composition of Claim 1 characterized in that plasticizer (D) of the polyester-system ion-conducting polymer (B) is a plasticizer represented by formula (1)



wherein m is an integer of 1-3, n is an integer of 4-25, A is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, B is a C<sub>1</sub>-C<sub>10</sub> alkyl, acyl, or aroyl, and X is H, CH<sub>3</sub>, or C<sub>2</sub>H<sub>5</sub>.

4. The antistatic polymer composition of Claim 1 characterized in that it

AMENDED SHEET

contains 40.0-98.4 wt% of polymer (A), 1.0-35.0 wt% of ion-conductive polyether-based polymer (B), 0.1-15.0 wt% of ion source (C), and 0.5-10.0 wt% of plasticizer (D) with respect to the weight of the composition as a whole.

5. Moldings characterized in that they are molded from the antistatic polymer composition of Claim 1.
6. Transfer medium-separating guide parts for electrophotographic devices characterized in that they are molded from the antistatic polymer composition of Claim 1.
7. A molded article made from the composition of claim 4 having surface resistivity in the range of  $10^7$  to  $10^{13}$  ohms, as measured under ASTM D 257 and being applied an electrostatic painting directly on surface thereof.
8. An antistatic polymer composition characterized in that it comprises
  - (A) one or more polymers selected from the group consisting of ABS (acrylonitrile butadiene styrene), polyethylene, polypropylene, polypropylene copolymer and EPDM(ethylene/propylene/diene) elastomer;
  - (B) a polyether-system ion-conducting polymer;
  - (C) an ion source comprising: (i) a source of at least one carboxyl group or sulfo group being selected from the group consisting of hydrocarbon acids containing 6-54 carbon atoms, sulfonic acids and organic polymers with at least one carboxyl group or sulfo group and (ii) a source of at least one metal ion that is selected from the group consisting of sodium ion, potassium ion, ammonium ion, lithium ion, magnesium ion, calcium ion, copper ion, and zinc ion and that can react with the carboxyl groups or sulfo group of (i), solid electrolytes or polymer electrolytes ; and
  - (D) a plasticizer of the aforementioned ion-conductive polyether-based polymer (B).
9. The composition of Claim 1 further comprising water-repellent

comprising fluorinated compounds, silicon compound or a mixture thereof .

10. A molded article made from the composition of Claim 8.

**DECLARATION and POWER OF ATTORNEY**

As a below-named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

**ANTISTATIC POLYMER COMPOSITION AND MOLDINGS THEREOF**

the specification of which is attached hereto unless the following box is checked:

☒ was filed on **23 DECEMBER 1998** as U.S. Application No. \_\_\_\_\_ or PCT International Application No.**PCT/US98/27428** and was amended on \_\_\_\_\_ (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is known to me to be material to patentability as defined in 37 CFR § 1.56.

I hereby claim foreign priority benefits under 35 U.S.C. § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate, or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

Application No.	Country	Filing Date	Priority Claimed (Yes/No)
9-366003	JAPAN	24 DECEMBER 1997	Yes

I hereby claim the benefit under 35 U.S.C. § 119(e) of any United States Provisional Application(s) listed below.

U.S. Provisional Application No.	U.S. Filing Date

I hereby claim the benefit under 35 U.S.C. § 120 of any United States application(s), or § 365(c) of any PCT International Application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application or PCT International Application in the manner provided by the first paragraph of 35 U.S.C. § 112, I acknowledge the duty to disclose information which is known to me to be material to patentability as defined in 37 CFR § 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application.

Application No.	Filing Date	Status (patented, pending or abandoned)

**POWER OF ATTORNEY:** I hereby appoint the following attorney(s) and/or agent(s) the power to prosecute this application and transact all business in the Patent and Trademark Office connected therewith:Name: **PHAM, HANH P.** Registration No.: **40,771**

Send correspondence and direct telephone calls to:

**PHAM, HANH P.****E. I. du Pont de Nemours and Company**  
**Legal - Patents**  
**Wilmington, DE 19898, U.S.A.**Tel. No.  
**(302) 992-4929**

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

**INVENTOR(S)**

<b>Full Name of Inventor</b>	<b>Last Name</b> <b>KOBAYASHI</b>	<b>First Name</b> <b>TOSHIKAZU</b>	<b>Middle Name</b>
	Signature (please sign full name): <i>Toshikazu Kobayashi</i>		Date: <i>Feb. 17 '99</i>
<b>Residence &amp; Citizenship</b>	<b>City</b> <b>KAWACHI-GUN TOCHIGI JPN</b>	<b>State or Foreign Country</b> <b>JAPAN</b>	<b>Country of Citizenship</b> <b>JAPAN</b>
<b>Post Office Address</b>	<b>Post Office Address</b> <b>3759-7 KAWACHI-MACHI</b>	<b>City</b> <b>KAWACHI-GUN TOCHIGI</b>	<b>State or Country</b> <b>JAPAN</b>
			<b>Zip Code</b> <b>329-1104</b>

☐ Additional Inventors are being named on separately numbered sheets attached hereto.

GENERAL POWER OF ATTORNEY  
(Concerning Several International Patent Applications)

The undersigned, Vernon R. Rice, Vice President and Assistant General Counsel of E. I. DU PONT DE NEMOURS AND COMPANY, 1007 Market Street, Wilmington, Delaware 19898 USA ("DuPont"), hereby confirms that the power to sign for DuPont has been granted to various individuals (as set forth in the attached excerpt from DuPont's Patent Board Rules of Procedure (January 1988), Appendix Section III.A.4), including the Chairman, Vice-Chairman, and those individuals who are Assistant Secretaries of the Patent Board. Currently these Assistant Secretaries are:

Roger A. Bowman  
Linda J. Davis  
John E. Griffiths

Miriam D. Meconnahey  
Dorothy W. Shafer  
Deborah A. Meginniss

In addition, the authority to act on behalf of DuPont before the competent International Authorities in connection with any and all international patent applications filed by it with the United States as Receiving Office and to make or receive payments on its behalf is hereby granted to:

Beardell, Lori Y.	34,293	Katz, Elliott A.	26,396
Belopolsky, Inna	43,319	Kelly, Patricia L.	39,247
Benjamin, Steven C.	36,087	King, Karen K.	34,850
Birch, Linda D.	38,719	Kuller, Mark D.	31,925
Bowen, Jr., Alanson G.	24,027	Krukiel, Charles E.	27,344
Christenbury, Lynne M.	30,971	Jarnholm, Arne R.	30,396
Cotreau, William J.	36,490	Langworthy, John A.	32,255
Deitch, Gerald E.	30,457	Lerman, Bart E.	31,897
Deshmukh, Sudhir	33,677	Levitt, Cary A.	31,848
Dobson, Kevin S.	40,296	Magee, Thomas H.	27,355
Duffy, Roscanne R.	33,869	Mayer, Nancy S.	29,190
Edwards, Mark A.	39,542	Medwick, George M.	27,456
Estrin, Barry	26,452	Morrissey, Bruce W.	30,663
Evans, Craig H.	31,825	Santopietro, Lois A.	36,264
Fair, Tamera L.	35,867	Schaeffer, Andrew L.	33,605
Feltham, S. Neil	36,506	Sebree, Chyrrea J.	45,348
Floyd, Linda Axamethy	33,692	Shafer, Robert J.	24,437
Frank, George A.	27,636	Shay, Lucas K.	34,724
Golian, Andrew G.	25,293	Shipley, James E.	32,003
Gorman, Thomas W.	31,959	Siegehl, Barbara C.	30,684
Gould, David J.	25,338	Sinnott, Jessica M.	34,015
Griffiths, John E.	32,647	Steinberg, Thomas W.	37,013
Hamby, Jane O.	32,872	Stevenson, Robert B.	26,039
Hamby, William H.	31,521	Strickland, Frederick D.	39,041
Heiser, David E.	31,366	Tessari, Joseph A.	32,177
Hendrickson, John S.	30,847	Tulloch, Rebecca W.	36,297
Jones, Brian C.	37,857	Walker, P. Michael	32,602
Joung, J. Kenneth	41,881	Wang, Chen	38,650

The undersigned ratifies fully all actions already taken by the above-named individuals in accordance with the authority granted hereby.

E. I. DU PONT DE NEMOURS AND COMPANY

By: \_\_\_\_\_

Vernon R. Rice

Vice President and Assistant General Counsel

Date: \_\_\_\_\_

5.11.2000